

## Sputter tool – Sys & Design

- Depositing: ZnO, V<sub>2</sub>O<sub>5</sub>
- Sample Sizes: 1 ~ 2 inches
- Target Size: 2 inches
- Base Pressure: ~ 10<sup>-6</sup> Torr
- Pump Time: ~ 2 Hours
- Operation Gas: Argon
- RF sputtering

